



Consommation
et Corporations Canada

Consumer and
Corporate Affairs Canada

Bureau des brevets

Patent Office

Ottawa, Canada
K1A 0C9

(11) (C)	1,298,479
(21)	525,469
(22)	1986/12/16
(45)	1992/04/07
(52)	71-47
C.L. CR.	167-164
	167-321

(51) INTL.CL. ⁵ A01N-25/34; A01N-25/10

(19) (CA) **CANADIAN PATENT** (12)

(54) System for the Controlled-Rate Release of Active
Substances

(72) Colombo, Paolo , Italy
La Manna, Aldo , Italy
Conte, Ubaldo , Italy

(73) Jagotec AG , Switzerland

(30) (IT) Italy 23321 A/85 1985/12/20

(57) 5 Claims

Canada

525457
1298479

ABSTRACT

A system for the controlled-rate release of active substances, consisting of:

- a) a deposit-core comprising the active substance and having defined geometric form;
- b) a support-platform applied to said deposit-core.

Said deposit-core contains, mixed with the active substance, a polymeric material having a high degree of swelling on contact with water or aqueous liquids, a gellable polymeric material, said polymeric materials being replaceable by a single polymeric material having both swelling and gelling properties, and other adjuvants able to provide the mixture with suitable characteristics for its compression and for its intake of water.

Said support-platform consists of a polymeric material insoluble in aqueous liquids and partially coating said deposit-core.

The intensity and duration of the swelling force of said polymeric material with a high degree of swelling constitutes the primary factor in controlling the release of the active substance.

This invention relates to a system able to release a contained active substance at a practically constant controlled rate into a fluid able to cause swelling of the deposit-core containing the active substance.

The active substance to be released can consist of pesticides, herbicides, fertilizers, room deodorants, medicaments and generally any type of substance which requires to be released at a controlled rate into a aqueous fluid.

Releasing an active substance at a practically constant rate from the system containing it enables accuracy and selectivity of action, administration reduction and optimum overall utilization to be obtained for the active substance, with both practical and economical advantages.

For example, in agriculture an insecticide or parasiticide activity can be obtained for prolonged time periods programmable in relation both to the specific requirements and to the existing or predicted moisture and temperature conditions.

Systems for the controlled release of active substances are used in many sectors of application, as stated heretofore, however the sector in which this requirement is particularly felt is that involving the administration of medicaments both in human and in veterinary therapy.

X



In this respect, particularly in the treatment of chronic illnesses with active substances having a short half-life, the therapy requires very frequent administration (4-5 times per day), which is poorly supported by the patient and can become
5 aleatory in its results.

To obtain greater posological simplicity and increase the acceptability of the administration scheme by the patient, so-called "delayed-action" pharmaceutical forms which can require
10 only one administration per day have been conceived and used in therapy.

The most advanced of these forms is known as a "therapeutic system", and consists of the following essential parts:

- 15 a) the medicament,
- b) a release module comprising a deposit of the medicament; the control element, the energy source and the release surface,
- c) a platform for keeping the system in seat,
- d) the therapeutic programme

20 The studies and implementations of these systems have mainly involved active principles which are soluble or very soluble in water, and are transferred by the pharmaceutical forms in which they are carried after dissolution. In these implementations,
25 the initial dissolution stage of the active principle is slowed down to such an extent as to control the absorption of the active substance. The operation of some of these systems is influenced considerably by the hydrodynamic conditions of the environment into which the system is inserted (stomach, intestine etc.).
30 Moreover, in the case of many of them the quantity of substance in the deposit has to be oversized relative to requirements because its release is incomplete.

Those implementations involving the release of medicaments which
35 are poorly soluble in water or in biological fluids are also completely inadequate, and there also remains unsolved the problem of simultaneously releasing from a single system two or

more active substances of different solubility, for which simultaneous transfer at equal or different rates is required.

5 An example of systems of the known art is described in Japanese patent application No. 065688 published October 29, 1984.

10 The drawbacks encountered with systems of the known art are obviated by the system according to the present invention, which also has the advantage of allowing controlled-rate release, in particle form, of substance practically insoluble in water.

15 This system is based on controlling the release of the active substances by the swelling which the deposit-core containing it undergoes when it comes into contact with water or with aqueous liquids.

According to the present invention there is provided a system for the controlled-rate release of active substances, consisting of: a deposit-core comprising the active substance and having defined geometric form, and a support-platform
20 applied to said deposit-core, characterized in that said deposit core contains, mixed with the active substance a) at least a polymeric material having high degree of swelling on contact with aqueous liquids, selected from the group consisting of: cross-linked sodium carboxymethylcellulose,
25 cross-linked hydroxypropylcellulose, high-molecular weight hydroxypropylmethylcellulose, carboxylmethanamide, potassium methacrylatedivinylbenzene copolymer, polymethylmethacrylate, cross-linked polyvinylpyrrolidone and high-molecular weight polyvinylalcohols, and b) at least a polymeric material
30 gellable in aqueous liquids, selected from the group consisting of: methylcellulose, carboxymethylcellulose, low-molecular weight hydroxypropylmethylcellulose, low-molecular

weight polyvinylalcohols, polyoxyethyleneglycols and non-cross linked polyvinylpyrrolidone, said polymeric material a) being in amount of 5% + 80% by w. of the total weight of the deposit-core and said polymeric material b) being in amount
5 of 90% + 10%, and further characterized in that said material b of the support-platform consists of a polymeric material insoluble in aqueous liquid and partially coating said deposit-core, said polymeric insoluble material being selected from polyacrylates, cellulose, methylcellulose,
10 cellulose acetate-propionate, polyethylene, polymethacrylates, acrylic acid copolymers and high-molecular weight polyvinylalcohols.

These and further characteristics and advantages of the system according to the invention will be more apparent from
15 the detailed description of preferred embodiments of the invention given hereinafter by the way of non-limiting example. The deposit-core is generally obtained by compressing the mixture containing

the active substance to a pressure of between 1000 and 4000 kg/cm², to thus assume a defined geometric form.

Polymeric materials having a high degree of swelling are essentially generally cross-linked insoluble polymers, whereas gellable polymeric materials are soluble, their purpose being to control the intake of water.

Polymers having a high degree of swelling comprise, inter alia, cross-linked sodium carboxymethylcellulose, cross-linked hydroxypropylcellulose, high-molecular weight hydroxymethylpropylcellulose, carboxymethylamide, potassium methacrylate-divinylbenzene copolymer, polymethylmethacrylate, cross-linked polyvinylpyrrolidone, high-molecular weight polyvinylalcohols etc. Gellable polymers include methylcellulose, carboxymethylcellulose, low-molecular weight hydroxypropylmethylcellulose, low-molecular weight polyvinylalcohols, polyoxyethyleneglycols, non-cross linked polyvinylpyrrolidone etc. Polymers simultaneously possessing swelling and gelling properties include medium-viscosity hydroxypropylmethylcellulose and medium-viscosity polyvinylalcohols.

The coating platform consists of a polymeric material insoluble in water and in possibly biodegradable biological liquids, and able to maintain its impermeability characteristics at least until the complete transfer of the active substance contained in the deposit-core. It is applied to a part of the external deposit-core surface chosen such as to suitably direct and quantitatively regulate the release of the active substance. In this respect, as the support-platform is impermeable to water, the polymeric material of the deposit-core can swell only in that portion of the deposit not coated with the platform.

The support-platform can be obtained by compressing prechosen polymeric materials onto the deposit-core, by immersing the deposit-core in a solution of said polymeric materials in normal organic solvents, or by spraying said solutions. Polymeric

materials usable for preparing the support-platform can be chosen from the class comprising acrylates, celluloses and derivatives such as ethylcellulose, cellulose acetate-propionate, polyethylenes and methacrylates and copolymers of acrylic acid, 5 polyvinylalcohols etc.

This platform can have a thickness of between 2 mm if applied by compression, and 10 microns if applied by spraying or immersion, and comprises from 10 to 90% of the total surface of the system. 10

The primary factor in controlling the release of the active substance is the intensity and duration of the swelling force developed by the swellable polymeric materials contained in the deposit-core on contact with aqueous fluids. In this respect, 15 the energy for activating, executing and regulating the release of the active substance is determined by the swelling force developed in the deposit-core when this comes into contact with water or with biological liquids. Said force has an intensity and duration which vary in relation to the type and quantity of 20 the polymeric materials used in formulating the deposit, and it lies between limits having a maximum value which occurs in the case of a deposit mainly containing the swellable polymer, and a minimum value which occurs in the case of a deposit mainly containing the gellable polymer.

25 Said swellable polymer is present to the extent of between 5 and 80% by weight, and said gellable polymer to the extent of between 90 and 10% by weight, with respect to the mixture forming the deposit-core.

30 A further control factor is the geometry of the support-platform, which limits the swelling of the deposit and directs the emission of material from it.

35 Within the scope of the present invention it is possible to conceive many systems for the controlled release of active substances, which base their operation on the swelling force and

differ from each other by the type of support-platform used.

Some embodiments are described by way of non-limiting example hereinafter, and their morphology and operation are illustrated
5 in detail in the relative examples.

1st case: system with one flat, concave or convex support-platform.

In its simplest form, the system consists of :

- 10 a) a deposit-core obtained by compression and containing the active principle and the swellable and gellable polymeric materials together with other components for making the mixture more easily compressible or for regulating water intake.
- 15 This deposit-core can generally have a geometric form similar to a cylindrical tablet with flat, convex or concave faces;
- b) a support-platform obtained by coating a base of the deposit-core with a layer of polymeric material, or a polymeric
20 material mixture, which is inert and insoluble in the medium into which the active substance is to be transferred.

The control factor is the deposit-core composition (weight ratio of swellable to gellable polymers), which is chosen in such a
25 manner as to obtain the desired swelling and thus the desired transfer rate of active substance. The platform limits the swelling of the deposit and directs the emission of active substance practically through 180°.

- 30 The structure of the system when dry, after hydration and when spent is shown in Figures 1, 2 and 3 respectively.

On contact with water or aqueous liquids, the system offers a large transfer surface, and for this reason is suitable for
35 poorly soluble/soluble medicaments (water solubility between 1 g/litre and 33 g/litre).

2nd case: system with two parallel flat or concave support-platforms.

In its simplest form, the system consists of:

a) a deposit-core obtained as described for the 1st case;

5

b) a support-platform obtained by coating the two bases of the deposit with a layer of polymeric material, or a polymeric material mixture, which is inert and insoluble in the medium into which the active substance is to be transferred.

10

The control factor is the deposit-core composition (weight ratio of swellable to gellable polymers).

The platform limits the swelling of the deposit, and directs the
15 emission of active substance practically in a radial direction.

The structure of the system when dry, after hydration and when spent is shown in Figures 4, 5 and 6 respectively.

20 On contact with water or aqueous liquids, the system offers a small transfer surface, and for this reason is suitable for soluble/very soluble medicaments (water solubility between 5 g/litre and 1000 g/litre).

25 3rd case: system with a container-shaped support-platform.

In its simplest form, the system consists of:

a) a deposit-core obtained as described for the 1st case;

b) a support-platform obtained by coating one base and the
30 lateral surface of the deposit with a layer of polymeric material, or a polymeric material mixture, which is inert and insoluble in the medium into which the active substance is to be transferred.

35 The control factor is the deposit composition (weight ratio of swellable to gellable polymers). The platform limits the swelling of the deposit, and directs the emission of active

substance practically in a direction perpendicular to the platform base.

The structure of the system when dry, after hydration and when spent is shown in Figures 7, 8 and 9 respectively.

On contact with water or aqueous liquids, the system offers a constant transfer surface. The system is suitable for practically insoluble, poorly soluble and very soluble medicaments (water solubility between 0.01 g/litre and 1000 g/litre).

A system of this latter type having a deposit consisting of 78% of swellable polymer and 13% of gellable polymer develops the swelling force given in column a) of Table I.

The same system but with a deposit consisting of 30% of a both swellable and gellable polymer develops the swelling force given in column b) of Table I.

20

TABLE I

Time (hours)	Swelling force (N)	
	a	b
0.5	39	12
1	30	10
2	20	5
4	8	0.6

4th case: system with a support-platform which laterally surrounds it.

In its simplest form, the system consists of:

a) a deposit-core obtained as described for the 1st case;

A particular case is that of a deposit of cylindrical or other geometric form composed of two portions obtained by double compression, in which the upper portion contains one medicament and the lower portion contains another.

b) a support-platform obtained by coating the lateral surface of

the deposit with a layer of polymeric material, or a polymeric material mixture, which is inert and insoluble in the medium into which the active substance is to be transferred.

5

The control factor is the deposit-core composition (weight ratio of swellable to gellable polymers). The platform limits the swelling of the deposit, and directs the emission of active substance or of the two active substances in two opposing
10 directions.

The structure of the system when dry, after hydration and when spent is shown in Figures 10, 11 and 12 respectively.

15 On contact with water or aqueous liquids, the system offers a large transfer surface, and for this reason is suitable for poorly soluble/soluble medicaments (water solubility between 0.1 g/litre and 100 g/litre) or for the simultaneous transfer of two different medicaments at the same rate or at different rates.

20

5th case: system with a support-platform covering one half of its surface

In its simplest form, the system consists of:

a) a deposit-core obtained as described for the 1st case;

25

b) a support-platform obtained by coating one half of the deposit surface with a layer of polymeric material, or a polymeric material mixture, which is inert and insoluble in the medium into which the active substance is to be
30 transferred.

The control factor is the deposit-core composition (weight ratio of swellable to gellable polymers).

35 The platform limits the swelling to one half of the deposit.

The structure of the system when dry, after hydration and when

spent is shown in Figures 13, 14 and 15 respectively.

On contact with water or aqueous liquids, the system offers a large transfer surface in the uncoated portion and a more limited transfer surface in the coated portion, and for this reason is suitable for medicaments which require high initial release followed slower release.

In the following examples the words "eudragit", "methocel" and "soitax" are trade marks.

EXAMPLE 1

Preparation of therapeutic systems in accordance with the procedures described for the 1st and 2nd cases.

a - Preparation of the deposit-core.

1000 deposit-cores were prepared using the following materials in the stated quantities:

diltiazem	45.0 g
hydroxypropylmethylcellulose (methocel K 100M-Colorcon)	35.0 g
mannitol	10.0 g
ethylcellulose (high viscosity-BDH)	3.75 g
magnesium stearate	1.0 g
5:1 95° ethanol-chloroform mixture	75.0 ml

The diltiazem was mixed intimately with the mannitol and hydroxypropylmethylcellulose in a suitable mixer. The solution of ethylcellulose in ethanol-chloroform was prepared separately, and was used for wetting the previously obtained powder mixture. The resultant homogeneous mass was forced through an 800 micron screen and then dried to obtain a granulate which was passed through a 420 micron screen. The homogeneous granulate

X

1298479

- 10a-

obtained was mixed with the magnesium stearate and then compressed using concave punches of diameter 7 mm (radius of curvature 9 mm) using a pressure of about 3000 kg/cm² to obtain cylindrical deposit-cores with convex bases.

b - Application of the support-platform.

The support-platform was applied by coating one or both the convex bases of the deposit-core with a solution of:

low-permeability acrylic-methacrylic copolymer

(eudragit RS Rohm Pharma)

15 g

5 in methylene chloride of a quantity to make up to 100 ml

0.3 ml of said solution were applied to each base to be covered, taking care to protect the lateral core surface.

10 The system was then dried with tepid air. The quantity of polymeric material deposited was sufficient to keep the structure intact during transfer.

c - "In vitro" transfer of the active principle.

15 The "in vitro" transfer tests were carried out both on the deposit-core (uncoated) and on the therapeutic systems complete with their support-platform. For this type of test, the USP XXI basket dissolving apparatus was used, the transfer fluid being 1000 ml of distilled water at 37°C.

20 The following results were obtained:

- transfer of diltiazem from the deposit-core (uncoated)

	time (min)	cumulative fraction transferred
	30	0.27
	60	0.39
25	120	0.57
	180	0.72
	240	0.83

- transfer of diltiazem from the deposit anchored to one concave platform (1st case)

	time (min)	cumulative fraction transferred
	30	0.22
	60	0.34
	120	0.51
35	180	0.66
	240	0.77
	360	0.94

- transfer of diltiazem from the deposit anchored to two parallel platforms (2nd case)

	time (min)	cumulative fraction transferred
	60	0.25
5	120	0.41
	180	0.56
	240	0.68
	300	0.78
	360	0.86

10

The release kinetics expressed by the equation:

fraction released = $K \times (\text{time})^n$ were as follows:

- deposit-core: fraction released = $0.48 \times (\text{time})^{0.51}$
- system of 1st case: fraction released = $0.32 \times (\text{time})^{0.57}$
- 15 - system of 2nd case: fraction released = $0.012 \times (\text{time})^{0.71}$

EXAMPLE 2

Preparation of therapeutic systems by the procedures described for the 3rd case.

20

a - Preparation of the deposit-core.

1000 deposit-cores were prepared using the following materials in the stated quantities:

	nifedipine	20 g
25	sodium carboxymethylcellulose (ACDISOL-FMC)	180 g
	hydroxypropylmethylcellulose (methocel K4M-Colorcon)	30 g
	magnesium stearate	1 g

30

- The nifedipine was mixed with acdisol for 30 minutes in a suitable mixer, methocel K4M and magnesium stearate were added, and mixing was continued for a further 30 minutes. Tablets (diameter 20 mm) were obtained by compression, and
- 35 were then ground in a swinging arm granulator to obtain a granulate which passed through a 600 micron screen. The granulate obtained was compressed by punches of diameter 9.5

mm to a pressure of 3000 kg/cm² to obtain cylindrical deposit-cores.

b - Application of the support-platform.

- 5 The platform was applied by coating one base and the lateral surface of the cylindrical deposit with a solution of:
- | | |
|------------------------------|--------|
| cellulose acetate propionate | |
| (CAP 482-20 Eastman-Kodak) | 15 g |
| castor oil | 1 g |
| 10 acetone | 100 ml |

The deposit-core was immersed in a polymeric solution as far as the edge of its upper base, and was then dried in a stream of tepid air. The quantity of solution applied was 1.5 ml.

15

c - "In vitro" transfer of the active principle.

The "in vitro" transfer tests were carried out with the continuous-flow SOITAX (CH) dissolving apparatus, operating with distilled water at 37° at a throughput of 17 ml/min.

20

The following results were obtained:

- transfer of nifedipine from the system

	time (min)	cumulative fraction transferred
	60	0.091
25	120	0.180
	180	0.260
	300	0.440
	360	0.520

- 30 The release kinetics are expressed by the zero-order equation: fraction released = 0.0014 x time + 0.0053

EXAMPLE 3

Preparation of therapeutic systems by the procedure described for
35 the 4th case.

a - Preparation of the deposit-core.

1000 deposit-cores were prepared using the following materials in the stated quantities:

Blue granulate

	diazepam	5 g
5	anhydrous citric acid	10 g
	mannitol	77.75 g
	methocel K4M	7.5 g
	methocel K15M	7.5 g
	polyvinylpyrrolidone	2 g
10	blue colouring (FCD n 3)	0.25 g
	magnesium stearate	1 g
	95° ethanol	40 ml

White granulate

15	octatropine methylbromide	60 g
	mannitol	33 g
	methocel K4M	7.5 g
	methocel K15M	7.5 g
	polyvinylpyrrolidone	2 g
20	magnesium stearate	1 g
	95° ethanol	40 ml

The two granulates were prepared in an analogous manner by the following procedure: the polyvinylpyrrolidone was dissolved in the ethanol whereas the other components, with the exception of the magnesium stearate, were mixed together intimately. The powder mixture was mixed with the polyvinylpyrrolidone solution and forced through a 600 micron screen, the obtained granules being mixed with the magnesium stearate after drying. Two granulates were thus produced, one white and one blue. The two granulates were poured separately into the hoppers of a compressing machine for double-layer tablets and compressed to 3000 kg/cm² with 7 mm diameter punches to obtain a type of deposit-core of cylindrical form with two superimposed coloured layers.

b - Application of the support-platform.

The platform was applied by coating the lateral surface of the cylindrical deposit with a solution of:

acrylic-methacrylic copolymer

	(eudragit RS)	24 g
5	castor oil	1 g
	acetone	50 ml
	isopropanol	50 ml

10 The deposit-core was coated on its lateral surface by spraying or brushing the polymeric solution, which was then dried in a stream of tepid air. The quantity of solution applied was 0.7 ml.

c - "In vitro" transfer of the active principle.

15 The "in vitro" transfer tests were carried out with the USP XXI basket dissolving apparatus, operating in 1000 ml of distilled water at 37°C at a rotation speed of 150 rpm.

The following results were obtained:

20 - transfer of octatropine methyl bromide and diazepam from the system.

	time (min)	cumulative fraction transferred	
		octatropine	diazepam
	30	0.13	0.12
25	60	0.24	0.23
	120	0.41	0.33
	180	0.56	0.51
	240	0.70	0.62

30 The release kinetics, expressed by the equation:

fraction released = $K \times (\text{time})^n$

were as follows:

diazepam fraction released = $0.012 \times (\text{time})^{0.71}$

octatropine fraction released = $0.011 \times (\text{time})^{0.76}$

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A system for the controlled-rate release of active substances, consisting of: a deposit-core comprising the active substance and having defined geometric form, and a support-platform applied to said deposit-core, characterized in that said deposit core contains, mixed with the active substance a) at least a polymeric material having high degree of swelling on contact with aqueous liquids, selected from the group consisting of: cross-linked sodium carboxymethylcellulose, cross-linked hydroxypropylcellulose, high-molecular weight hydroxypropylmethylcellulose, carboxylmethylamide, potassium methacrylatedivinylbenzene copolymer, polymethylmethacrylate, cross-linked polyvinylpyrrolidone and high-molecular weight polyvinylalcohols, and b) at least a polymeric material gellable in aqueous liquids, selected from the group consisting of: methylcellulose, carboxymethylcellulose, low-molecular weight hydroxypropylmethylcellulose, low-molecular weight polyvinylalcohols, polyoxyethyleneglycols and non-cross linked polyvinylpyrrolidone, said polymeric material a) being in amount of 5% + 80% by w. of the total weight of the deposit-core and said polymeric material b) being in amount of 90% + 10%, and further characterized in that said material (b) of the support-platform consists of a polymeric material insoluble in aqueous liquid and partially coating said deposit-core, said polymeric insoluble material being selected from polyacrylates, cellulose, methylcellulose, cellulose acetate-propionate, polyethylene, polymethacrylates, acrylic acid copolymers and high-molecular weight polyvinylalcohols.

2. A system as claimed in claim 1, characterized in that said support-platform is formed by applying said water-


insoluble polymeric material to said deposit-core by compression.

5 3. A system as claimed in claim 1, characterized in that said support platform is formed by immersing said deposit-core in a solution of said water-insoluble polymeric material in an organic solvent.

10 4. A system as claimed in claim 1, characterized in that said support-platform is formed by spraying said water-insoluble polymeric material in the form of a solution in an organic solvent onto the said deposit-core.

5. A system as claimed in claim 1, characterized in that said support-platform has a thickness of between 10 microns and 2 mm.





BEST AVAILABLE COPY

Marks & Clerk